

Red Ice 611HTC

High Temperature Stable Thermal Grease

DESCRIPTIONS

Red Ice 611HTC is specifically designed to eliminate compound “dry-out” problems due to the continuous exposure temperatures exceeding 200°C (392°F). This non-silicone thermal compound specially formulated for applications with continuous temperatures exceeding 200°C (392°F) and intermittent temperatures **up to 360°C (680°F)**. It shown outstanding stability and efficient heat transfer for the full operational life of your hardware.

Red Ice 611HTC offers high thermal conductivity and **high temperature stability up to 360°C (680°F)**. This thixotropic compound provides minimal out gassing, low bleed and evaporation.

KEY FUTURES AND BENEFITS

- **Rated Up to 360°C (680°F)**
- **High Thermal Conductivity (3.2 W/m-K)**
- Low Out-Gassing
- Re-workable, Low Bond Line Thickness

APPLICATIONS

- Heater cartridges, heating coil/plate, tank heater.
- Thermal sensors, TEC modules, Thermal Wells
- High power IGBT's, LED
- Power Transistors, Diodes, Power Resistors

AVAILABILITY

Syringes (3cc, 10cc, 30cc). Jars (8 oz & 1 Kg). Cartridges (6 oz. Semco & 300cc). 1 gallon & 5 gallon pail

Typical Property	Test Method	Results
Type		Silicone Free
Special Future		High Temperature Stable up to 360°C (680°F) High Thermal Conductivity
Color	Visual	Gray
Viscosity 50 rpm @ 25°C, PaS	Helipath	150
Specific Gravity	ASTM D792	3.2
Operating Temperature Range. °C		-55°C to 360°C
Out Gassing: % TML % CVCM	ASTM-E595 Internal Test data	0.90 0.01
Shelf Life @25C		5 years
THERMAL		
Thermal Conductivity (W/m-K)	ASTM D5470	3.2
Thermal Resistance °C-in ² /W	ASTM D5470	0.0016
ELECTRICAL		
Breakdown Voltage (KV/mm)	ASTM D149	3
Dissipation Factor (1KHz)	ASTM D150	0.12
Volume Resistivity (Ohm-cm)	ASTM D257	10 ¹⁰

DISCLAIMER: All statements, technical information, and recommendations related to Timtronics products are based on information believed to be reliable, but accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You must assume all risks and liability associated with such use. Timtronics will not be liable for any indirect, special, incidental or consequential loss or damage arising from this product, regardless of legal theory asserted.