

White Ice 515

Silicone Thermal Grease

DESCRIPTIONS

White Ice 515 is non-reactive; non-abrasive, ceramic based Thermally Conductive Grease with a high thermal conductivity and low thermal resistance. This product is formulated with specialty binding agents to achieve lowest amount of bleed and evaporations. It is designed for fiber optics applications where efficient thermal transfer required with zero abrasion. Offers excellent stability over wide temperature ranges. Easy to apply by dispensing or screen print/Stencil.

KEY FUTURES AND BENEFITS

- High Di-Electric Strength/Low constant
- Thermal Conductivity (**2.0 W/m-K**)
- Thixotropic Paste
- RoHS Compliant-Halogen Free
- Re-Workable

APPLICATIONS

- Fiber-Optics
- Thermal sensors, TEC modules, Thermal Wells
- IGBT's, LED
- Power Transistors, Diodes, Power Resistors
- CPU/GPU/Heat Sink

AVAILABILITY

Syringes (3cc, 10cc, 30cc). Jars (8 oz & 1 Kg). Cartridges (6 oz. Semco & 300cc).
1 gallon & 5 gallon pail

Typical Property	Test Method	Results
Type		Silicone
Special Future		Non-Abrasion type. High Thermal Conductivity High Di-Electric Strength-Low Di-Electric Constant
Color	Visual	White
Viscosity 5 rpm @ 25°C, PaS	Helipath	40
Specific Gravity	ASTM D792	2.0
Operating Temperature Range.°C		-55°C to 200°C
Shelf Life @25C		5 years
THERMAL		
Thermal Conductivity (W/m-K)	ASTM D5470	2.0
Thermal Resistance °C-in ² /W	ASTM D5470	0.017
ELECTRICAL		
Breakdown Voltage (KV/mm)	ASTM D149	16
Di-Electric Constant (1KHz)	ASTM D150	8
Dissipation Factor (1KHz)	ASTM D150	0.0026
Volume Resistivity (Ohm-cm)	ASTM D257	10 ¹⁴

DISCLAIMER: All statements, technical information, and recommendations related to Timtronics products are based on information believed to be reliable, but accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You must assume all risks and liability associated with such use. Timtronics will not be liable for any indirect, special, incidental or consequential loss or damage arising from this product, regardless of legal theory