

# TIM-LGF-2030

**Thermally Conductive, Two Part Silicone Liquid Gap Filler**

## DESCRIPTIONS

**TIM-LGF-2030** is thermally conductive liquid gap filler materials formulated to provide a balance of cured material properties with “gel-like” modules and good compression set or memory. This Form-in-Place liquid gap filler is ideal for applying any thickness. Unlike cured thermal pad, a liquid approach offers infinite thickness variations with little or no stress to sensitive components during assembly process..

**TIM-LGF-2030** flows under pressure like grease, easily cures at room or elevated temperature and form in soft rubber/gel and adheres to most surfaces, forms shapes and sizes of components with very low compression force. It eliminates multiple pad thickness and die-cut shapes for individual applications. It can be applied like grease, easily dispensable from wide range of commercially available equipment.

## KEY FUTURES AND BENEFITS

- **Thermal Conductivity ( 3.5 W/m-K)**
- Ultra-conforming, wet-out. Designed for fragile and low stress applications
- **Soft/Gel type cure. Low Hardness**
- Relieves CTE Stress during thermal cycling

## APPLICATIONS

- Interface for semiconductors requiring low pressure or spring clamp mounting
- Flip chip microprocessors, Graphic chips
- PPGA's, BGA, Micro BGA, DSP chips, LED
- Automotive electronics (ECU's)
- Thermally conductive vibration dampening

## AVAILABILITY

50cc & 400cc dual Syringes/Cartridges, 2 gallons & 10 gallons Kits

Property	Test Method	Value
Type		Two Parts Silicone, curable
<b>Special Futures</b>		<b>Soft, gel type cure, excellent deflection value</b>
Color	Visual	Green (Part A: White. Part B: Green)
Mixed Viscosity. PaS	Brookfield	400
Mix Ratio		1:1
Specific Gravity	ASTM D792	2.5
Hardness (Shore 00)	ASTM D2240	<b>35</b>
Pot Life @ 25°C		60 min
Cure Time @ 25°C		24-48 hrs
Cure Time @ 100°C		30 min
Flammability (Equivalent)	UL 94	V-0
Operating Temperature Range.		-55°C to 204°C
Shelf Life (Unopened)		12 months
<b>THERMAL</b>		
Thermal Conductivity (W/m-K)	ASTM D5470	<b>3.5</b>
<b>ELECTRICAL</b>		
Breakdown Voltage (KV/mm)	ASTM D149	13
Volume Resistivity (Ohm-m)	ASTM D257	10 <sup>12</sup>

**DISCLAIMER:** All statements, technical information, and recommendations related to Timtronics products are based on information believed to be reliable, but accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You must assume all risks and liability associated with such use. Timtronics will not be liable for any indirect, special, incidental or consequential loss or damage arising from this product, regardless of legal theory asserted.