

TIM-PC 8556

Thermally Conductive Silicone Potting Compound

DESCRIPTIONS

TIM-PC 8556 is a high temperature rated two parts thermally conductive low viscosity thixotropic compound which cures at room temperature or can be accelerated with heat. Specially designed to achieve low hardness and primer-less adhesion to substrates includes metals, plastics and ceramics. Excellent dielectric encapsulation and vibration absorption.

Applications: Potting and encapsulating of Equipment modules, Power supplies, relays and amplifiers, Transformers, coils and ferrite cores. Fiber optic wave guide coatings. Encapsulation of circuit boards

INSTRUCTION FOR USE

1. Thoroughly stir both parts prior to mixing together.
2. **Mixing by Hand:** Combine equal part of A & B components by weight, mix until completely mixed. Use care when mixing to minimize air entrapment. Avoid foreign contaminations.
3. **Mixing and dispensing with automated equipment:** Use properly ratio equipment (1:1), use mixing system that will properly mix part A & B. Mixed parts will have short pot life, refer data sheet.

Note: Refer to Safety Data Sheet (**SDS**) for additional health and safety information.

AVAILABILITY

2 Parts Kits: 2 gallon & 10 gallon pail.

Property	Results
Special Future	High Temperature rated up to 240°C. Meets UL94V0 Long pot life. Fast cure
Type	Two Parts
Mix Ratio by Weight (A/H)	1:1
Shelf Life	12 months@ 25°C
Mixed Viscosity @25°C cp	2000
Gel Time (Pot Life) (100 grams)	60-90 minutes
Cure Schedule	24-48 hr @ 25°C or 15 min @ 150°C
Cured Properties	
Color	Black
Specific Gravity	1.3
Hardness (Shore)	A-46
Tensile Strength	280psi
Elongation	75%
Service Temperature Range	-55°C to 240°C
THERMAL	
Thermal Conductivity (W/m-K)	0.40
ELECTRICAL	
Dielectric Strength (KV/mm)	17.5
Dielectric Constant	3.4
Volume Resistivity (Ohm-cm)	10 ¹⁵

DISCLAIMER: All statements, technical information, and recommendations related to Timtronics products are based on information believed to be reliable, but accuracy or completeness is not guaranteed. Before using this product, you must evaluate it and determine if it is suitable for your intended application. You must assume all risks and liability associated with such use. Timtronics will not be liable for any indirect, special, incidental or consequential loss or damage arising from this product, regardless of legal theory asserted.